

Technical Specifications

Technical characteristics:



Hardness

3



Porosity

0,2 %
EN 1936



Weight kg.

2700 kg/m³
EN 1936



Cold resistance



Abrasion resistance

22,0 mm
EN 14157



Bending resistance

12,6 MPa
EN 12372



Corrosion resistance

123,18 MPa
EN 1926



Water absorption

0,1 %
EN 13755