

Technical Specifications

Silver Pearl Marble

Apparent Density (kg/m ³)	2689
Water Absorption at Atmospheric Pressure (%)	%0,12
Compressive Strength (Mpa)	124,95
Modulus of Rupture (Mpa)	17,46
Compressive Strength After Heat Treatment (Mpa)	78,76