

Technical Specifications

	NORME TEST N°	DESCRIZIONE DESCRIPTION	VALORE A NORMA REQUIRED STANDARD	VALORE - LEV RESULTS - LEV	VALORE - MATT RESULTS - MATT
	ISO 10545/3	ASSORBIMENTO D'ACQUA WATER ABSORPTION ABSORPTION D'EAU WASSERAUFNAHME	$\leq 0,5\%$	CONFORME CONFORMS	CONFORME CONFORMS
	ISO 10545/4	RESISTENZA ALLA FLESSIONE BENDING STRENGTH RESISTANCE A LA FLEXION BIEGFESTIGKEIT	$R \geq 35 \text{ N/mm}^2$	CONFORME CONFORMS	CONFORME CONFORMS
	ISO 10545/8	COEFFICIENTE DI DILATAZIONE TERMICA LINEARE THERMAL EXPANSION COEFF. BETWEEN 20°C - 100°C COEFF. DE DILATATION THERMIQUE LINEAIRE ENTRE 20°C ET 100°C WÄRMEAUSSDEHNUNG ZWISCHEN 20°C UND 100°C	$\leq 9 \times 10^{-4}$	$9 \times 10^{-5} \text{ } ^\circ\text{C}^{-1}$	$9 \times 10^{-5} \text{ } ^\circ\text{C}^{-1}$
	ISO 10545/9	RESISTENZA AGLI SBALZI TERMICI RESISTANCE TO THERMAL SHOCK RESISTANCE AUX CHOCS THERMIQUES TEMPERATURWECHSELBESTÄNDIGKEIT		RESISTE RESISTANT RÉSISTE BESTÄNDIG	RESISTE RESISTANT RÉSISTE BESTÄNDIG
	ISO 10545/11	RESISTENZA AL CAVILLO CRAZING RESISTANCE RESISTANCE AU TRASSAILAGE HAARRISSFESTIGKEIT		RESISTE RESISTANT RÉSISTE BESTÄNDIG	RESISTE RESISTANT RÉSISTE BESTÄNDIG
	ISO 10545/14	RESISTENZA ALLE MACCHIE STAIN RESISTANCE RESISTANCE AUX TACHES FLECKENFESTIGKEIT	min. Classe 3	CONFORME CONFORMS	CONFORME CONFORMS
	ISO 10545/13	RESISTENZA ALL'ATTACCO CHIMICO CHEMICAL RESISTANCE RESISTANCE À L'ATTAQUE CHIMIQUE FÄHIG GEGEN SÄUREN UND LAUGEN	min. B	CONFORME CONFORMS	CONFORME CONFORMS
	ISO 10545/2	LUNGHEZZA E LARGHEZZA LENGTH AND WIDTH LONGUEUR ET LARGEUR LÄNGE UND BREITE	$\pm 0,5\%$	CONFORME CONFORMS	CONFORME CONFORMS
	ISO 10545/2	SPESSORE THICKNESS ÉPAISSEUR STÄRKE	$\pm 5\%$	CONFORME CONFORMS	CONFORME CONFORMS
	ISO 10545/2	ORTOGONALITÀ WEDGING ORTHOGONALITÉ RECHTWINKLICHKEIT	$\pm 0,6\%$	CONFORME CONFORMS	CONFORME CONFORMS
	ISO 10545/2	PLANARITÀ WARPAGE PLANÉITÉ EBENFLÄCHIGKEIT	$\pm 0,5\%$	CONFORME CONFORMS	CONFORME CONFORMS
	ISO 10545/12	RESISTENZA AL GELO FROST RESISTANCE RESISTANCE AU GEL FROSTBESTÄNDIGKEIT		RESISTE RESISTANT RÉSISTE BESTÄNDIG	RESISTE RESISTANT RÉSISTE BESTÄNDIG
	ISO 10545/6	RESISTENZA ALL'ABRASIONE PROFONDA DEEP ABRASION RESISTANCE RÉSISTENCE À L'ABRASION PROFONDE TIEFENVERSCHLEISSBESTÄNDIGKEIT	$< 175 \text{ mm}^3$	SILVER 148 mm^3 WHITE 143 mm^3	SILVER 143 mm^3 WHITE 128 mm^3
	ISO 10545/7	RESISTENZA ALL'ABRASIONE ABRASION RESISTANCE RÉSISTENCE À L'ABRASION ABRIEB		PEI IV	PEI IV
	BOT 3000 WET DCOF	RESISTENZA ALLO SCIVOLAMENTO SLIP RESISTANCE RESISTANCE AU GLISSEMENT BESTIMMUNG DER RUTSCHEMMENDE EIGENSCHAFT	$\geq 0,42$		Tile 1: 0,46 Tile 2: 0,45 Tile 3: 0,45
	DIN 51130 R	WATER, OIL, GREASE, ETC. CREATE SLIPPERY CON- DITIONS. FLOOR APPLICATIONS WITH EXPOSURE TO THESE CONDITIONS REQUIRE EXTRA CAUTION IN PRODUCT SELECTION.			R9