

Technical Specifications

E.N. 14411-ISO 13006 . Appendix G. Group Bla. UGL		Test method	Reference value	Declared value
	Dynamic coefficient of friction (section 9.6 ANSI A 137.1 2012)	DCOF	>0,42 wet	> 0,42 wet MATTE
	Slip resistance with shoes	DIN-EN-16165- ANNEX-B	-	R9 MATTE
	Length and width: admitted deviation, in %, of the average size of each tile from the production dimensions	ISO-10545-2	Squadrato ISO 13006 - $\pm 0,3\%$ (± 1 mm)	$\pm 0,15\%$
	Maximum right-angle deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	Squadrato ISO 13006 - $\pm 0,3\%$ ($\pm 1,5$ mm)	$\pm 0,2\%$
	Flatness (centre curvature / edge curvature / warpage)	ISO-10545-2	Squadrato ISO 13006 - $\pm 0,4\%$ ($\pm 1,8$ mm)	$\pm 0,35\%$
	Maximum straightness deviation, in %, in relation to the corresponding production dimensions	ISO-10545-2	Squadrato ISO 13006 - $\pm 0,3\%$ ($\pm 0,8$ mm)	$\pm 0,1\%$
	Admitted deviation, in %, of the average thickness of each tile from the production dimensions	ISO-10545-2	$\pm 5\%$ ($\pm 0,5$ mm)	$\pm 5\%$
	Surface quality	ISO-10545-2	Il 95% min delle piastrelle deve essere esente da difetti visibili / At least 95% of the tiles must be free from visible flaws / 95% min des carreaux ne doivent présenter aucun défaut visible / Mindestens 95% der Fliesen müssen frei von sichtbaren / mín. el 95% de las baldosas tiene que estar exento de defectos visibles	CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME / COOTBETCTBYET
	Amount of water absorbed, in percentage	ISO-10545-3	$E \leq 0,5\%$	average value 0,08%
	Bending strength in N/mm2	ISO-10545-4	>35 N/mm2	average value 50 N/mm2
	Breaking strength in N (thickness $\geq 7,5$ mm)	ISO-10545-4	≥ 1300 Newton	average value 3200 N
	Resistance to deep abrasion of unglazed tiles	ISO-10545-6	<175 mm3	average value 140 mm3
	Thermal shock resistance	ISO-10545-9	-	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ
	Frost resistance	ISO-10545-12	Richiesta / Required / Requisite / Gefordert / Requerida	RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ

Come dichiarato dal produttore / See

	Resistance to low concentrations of acids and alkali	ISO-10545-13	manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	ULB HIGH-GLOSSY
	Resistance to low concentrations of acids and alkali	ISO-10545-13	Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante	ULA-ULB MATTE
	Resistance to domestic chemicals and additives for swimming pools	ISO-10545-13	UB minimo / UB minimum / UB minimum / UB mindestens / UB minimo	UA
	Resistance to staining	ISO-10545-14	-	Cl. 5 MATTE
	Resistance to staining	ISO-10545-14	-	Cl. 4 HIGH-GLOSSY

